

S^pECtite RoofFlex Plus

COLD APPLIED ALIPHATIC POLYURETHANE

DESCRIPTION

SpECTite RoofFlex Plus is a single component moisture cure aliphatic polyurethane waterproofing liquid membrane.

TYPICAL USES

SpECTite RoofFlex Plus is suitable for waterproofing:

- Exposed Roofing
- Planter Boxes
- Swimming Pools
- Balconies
- Terraces
- Wood
- Metal Surfaces
- Exterior Masonry Building

ADVANTAGES

- High Tensile Strength
- Highly Elastic
- UV Resistance
- Hard-Wearing
- Durability
- Crack-Bridging

TECHNICAL DATA

Form	White
Tensile strength (ASTM D 412)	8.0 N/mm ²
Elongation (ASTM D 412)	> 700%
Tear Resistance (ASTM D 624)	> 15 N/mm
UV Resistance (ASTM D 822)	@ 1000 hours pass
SRI (Solar Reflectance Index) (ASTM E 1980)	101
Shore A Hardness (ASTM D 624)	>70

Resistance to Chemicals

(Visual Check) Limited Effect

**Permeability
(BS EN 12390)** Nil

APPLICATION INSTRUCTIONS

Surface Preparation

Surfaces must be dry and free from oil, dust, dirt, grease and loosing materials. The substrate should be firm, in case of gaps and cracks fill with suitable poly-sulphide sealant and ensure the surface is level.

For metal surface, clean the surface of all rust scales. This can be achieved by wire brushing or grit blasting.

Substrate Priming

Self-prime **SpECTite RoofFlex Plus** using 20% xylene. Insure proper spreading and coverage of Pinholes.

Application

Apply first coat of **SpECTite RoofFlex Plus** at a rate of 0.4 to 0.6 mm WFT.

Optional single reinforcement sheet fibre mesh or geotextile may be used for angle filling.

Apply the second coat at a rate of 0.4 to 0.6 mm or 0.6 to 0.7 mm where reinforcement sheet fibre mesh or geotextile is used.



PACKAGING & YIELD

SpECTite RoofFlex Plus is supplied in 18 litre drums.

The coverage rate for **SpECTite RoofFlex Plus** is 1.0 to 1.2 litre/m²/2 coats. Minimum 2 coats are required.

STORAGE & SHELF LIFE

SpECTite RoofFlex Plus has a shelf life of 12 months when stored in original containers in cool, dry conditions. Protect the material against moisture and direct sunlight. Storage temperature: 5°C to 35°C.

HEALTH & SAFETY

Contact with skin and eyes should be avoided. It is essential that adequate ventilation is provided and that all personnel avoid inhaling the vapours produced. If working is necessary in a confined area it is strongly recommended that sealed respiratory equipment is utilised.

Eye contact

Rinse with copious amounts of clean water and seek medical attention.

Skin contact

Rinse with copious amounts of clean water followed by thorough cleaning with soap and water.

DO NOT USE SOLVENTS

Ingestion

Seek immediate medical attention.

DO NOT INDUCE VOMITING.

Issue 3: 05/2025

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

If it is proven that the product does not perform as described in our TDS, SpEC's liability extends solely to the free replacement of product, once the claim has been accepted after due investigation by SpEC. SpEC will not entertain any claims involving any form of consequential costs or damages such as shipping costs, custom duties, damages to third parties, damages to structures, penalties from delay of a project or any other form of consequential damage.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696

E-mail: info@spec.ae

www.spec.ae