

SpECTop PRIMER EP121

MEDIUM VISCOSITY 2K SOLVENT-FREE EPOXY PRIMER FOR CONCRETE AND STEEL

DESCRIPTION

SpECTop Primer EP121 is a two-part, solvent-free, medium viscosity epoxy primer used prior to the application of Waterproofing, Sealants, Epoxy, PU coatings, and Floorings for concrete and steel surfaces.

TYPICAL USES

Excellent bonding on **Concrete/Steel**.

ADVANTAGES

- Solvent-free.
- Exceptional adhesion to concrete, steel and most of the common construction substrates.
- Formulated at 1:1 ratio by volume for easy mixing and application at site.

TECHNICAL DATA

Typical Properties @ 25±3°C

Appearance	Clear to Amber medium viscous when mixed
Touch Dry	6 - 10 hours
Solids by weight	~100%
Application Temperature - °C	05 - 40
Mixed density - Kg/m³	1050±50
Adhesion to concrete	Higher than the cohesive strength of concrete

METHOD OF APPLICATION

Surface Preparation

Remove the dust, dirt, oil, grease and any loose particles which may affect the bonding. for old concrete surface, remove existing coatings mechanically, and check for the soundness of concrete. Cracks and damaged areas should be

filled/repared using suitable cementitious/epoxy repairing materials and putties. For steel, grit blast the surface to SA 2 ½ profile.

Mixing and Application

SpECTop Primer EP121 is supplied as a pre-weighed 2 component pack. The contents of hardener pack should be emptied completely into the base pack and mixed with slow speed light duty mixing drill and paddle. Alternatively, for smaller quantity mixes, take equally quantities by volume from base and hardener, and mix with hand blender or a spatula. The mixed product can then be applied on to the prepared substrate using a brush or roller. Care should be taken at highly porous and critical areas, to apply with a brush at scribbling action.

EQUIPMENT CLEANING

SpECTop Primer EP121 may be removed with **SpECTop Cleaning Fluid** immediately after use.

Cured material can only be removed mechanically.

PACKAGING AND YIELD

SpETite Primer EP121 is supplied in 15 litre units. Application rate is 10-20 m²/l/coat with 50µ to 100µ thickness.

STORAGE AND SHELF LIFE

SpECTop Primer EP121 has a shelf life of 12 months when stored in original, unopened containers in a cool, dry environment.

HEALTH AND SAFETY

Contact with skin and eyes should be avoided.

FLAMMABILITY

SpECTop Primer EP121 is non-flammable.

Issue 1: 01/2024

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

If it is proven that the product does not perform as described in our TDS, SpEC's liability extends solely to the free replacement of product, once the claim has been accepted after due investigation by SpEC. SpEC will not entertain any claims involving any form of consequential costs or damages such as shipping costs, custom duties, damages to third parties, damages to structures, penalties from delay of a project or any other form of consequential damage.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696

E-mail: info@spec.ae

www.spec.ae